

NA STANDARD NO.	BASIC DIMENSIONS	SUBSTITUTE FORMED SECTION
1S14-32		
	Area: .037 sq. in.	Al. Alloy 24ST clad .032 x 1.155 x L Sheet Area: .037 sq. in.
1S14-40		
	Area: .046 sq. in.	Al. Alloy 24ST clad .040 x 1.144 x L Sheet Area: .046 sq. in.
1S14-64		
	Area: .072 sq. in.	Al. Alloy 24S0 clad .064 x 1.114 x L Sheet Area: .072 sq. in.
1S36-32		
	Area: .033 sq. in.	Al. Alloy 24ST clad .032 x 1.031 x L Sheet Area: .033 sq. in.
<p data-bbox="889 1755 1256 1871">NOTE: Heat-treat Al. Alloy 24S0 to 24ST after forming. All repair material to conform to specification AN-A-13.</p>		

FIGURE 8-2. ROLLED SECTION EQUIVALENTS (sheet 2 of 4 sheets)