

NA STANDARD NO.	ALCOA DIE NO.	BASIC DIMENSIONS	SUBSTITUTE FORMED SECTION
1E106T	14284	<p>Area: .327 sq. in.</p>	<p>Al. Alloy 2480 clad .156 x 2.576 x L Sheet Area: .402 sq. in.</p>
1E128T	31153	<p>Area: .121 sq. in.</p>	<p>Al. Alloy 2480 clad .102 x 1.547 x L Sheet Area: .1575 sq. in.</p>
1E129T	31154	<p>Area: .218 sq. in.</p>	<p>Al. Alloy 2480 clad .156 x 1.81 x L Sheet</p>
1E165T	32846	<p>Area: .663 sq. in.</p>	No substitution permitted

NOTE: Heat-treat Al. Alloy 2480 to 24ST after forming. All repair material to conform to specification AN-A-13.

FIGURE 8-1. EXTRUSION EQUIVALENTS (sheet 2 of 5 sheets)